

300 Eisenhower Lane N. Lombard, IL 60148 (630)495-2001 cs@saftlok.com www.saftlok.com

Grade AV Threadlocking Compound

Technical Data Sheet

TECHNICAL SUPPORT

Our technical support team stands ready to assist you with your technical questions regarding your SAF-T-LOK products. On-Site support when necessary within 24 hours.

PART NUMBERS

12321	10ml
12331	50 ml
12341	250ml
12343	1 liter

SPECIFICATIONS

MIL-S-22473

ASTM D5363

TURNKEY SOLUTIONS

As an ISO 9001:2015 certifed company, SAF-T-LOK can design or refine products to fit your company's specific needs and requirements.

For more information on any of our products or services please visit us on the Web at: www.saftlok.com

PRODUCT DESCRIPTION:

SAF-T-LOK Grade AV Threadlocker was developed to meet MIL-S-22473 for use where medium viscosity is needed to fill small gaps and high strength threadlocking is required.

GENERAL INFORMATION:

SAF-T-LOK anaerobic adhesives/sealants are a specialized series of single, solvent-free compounds that are individually formulated for locking, sealing, retaining and bonding metal parts and assemblies. Stable in the presence of air, these products cure when placed between mating metals parts, forming a resilient, vibration-proof, bonded seal.

SAF-T-LOK adhesives/sealants provide the user with additional performance characteristics, including resistance to corrosion or galvanic attack, as well as solvent resistance, while allowing disassembly with normal tools, if desired.

PRODUCT CHARACTERISTICS:

Color:	Red
Specific Gravity:	1.06 gm/cc
Viscosity:	100-250 cps
Flash Point:	>200°F
Temperature Range:	-65°F to 350°F
Storage Stability:	+ 12 months at <75°F

PERFORMANCE CHARACTERISTICS:

Locking Torque: Range Prevailing:	100-250 in. lb
Gap Filling:	Max. 0.005"
Full Cure:	8-24 hours

NOTE: This product is not recommended for use with pure oxygen systems.

Cure speed is dependant upon the gap to be filled. While MIL-S-22473 calls for cure in 24 hours, at 75°F this product is generally cured at 8 hours, on the 3/8-24 UNF steel fasteners specified. Somewhat longer cure would result if 3/8-16 UNF steel fasteners or plated fasteners were used. This product satisfies the requirements of MIL-S-22473E.

IMPORTANT NOTICE: All statements and technical data contained herein are based on tests we believe to be reliable, but the accuracy of completeness thereof is not guaranteed. It is recommended that the buyer test this product to determine its suitability for his application before use. **SAF-T-LOK International Corporation** is not responsible for loss, claim or damages resulting from use of its products.