

PRODUCT DESCRIPTION:

SAF-T-LOK RTV Silicone Sealant White replaces a wide range of cork, paper, asbestos, felt, and metal gaskets. Works on flanges, cover plates, gearbox closures and even conduit and threaded assemblies. Operating service temperatures from -62°F to 350°F. The product performs intermittently to 400°F. **SAF-T-LOK Silicone Sealants** are 100% solids and contain no extenders, thus shrinkage due to weathering is nil. They possess excellent resistance in U.V. ozone, smog, rain and snow. The product is VOC compliant. RTV color selection is dependent on actual application requirements.

ELECTRICAL PROPERTIES: SAF-T-LOK Silicone rubber sealants have excellent insulation properties when applied to electrical connections, etc.

TECHNICAL SUPPORT

Our technical support team stands ready to assist you with your technical questions regarding your SAF-T-LOK products. On-Site support when necessary within 24 hours.

PART NUMBERS

73122	3 oz
73148	7.25 oz
73163	10.3 oz
73179	4.5 gal

SPECIFICATIONS

ASTM C920 Type S, NS,

Class 25; TT-S-00230C,

TT-S-01543A,

MIL-A-46106A,

FDA CFR 177.2600,

USDA Approved, NSF 51,

UL Recognized Component.

TURNKEY SOLUTIONS

As an ISO 9001:2015 certified company, SAF-T-LOK can design or refine products to fit your company's specific needs and requirements.

For more information on any of our products or services please

visit us on the Web at:

www.saftlok.com

PHYSICAL PROPERTIES

TEST METHOD

PHYSICAL PROPERTIES		TEST METHOD
Cure System	Acetoxo	
Movement Capability, %	±25%	ASTM C-719
Modulus	Medium	ASTM D-412
Physical Properties (Cured)	Rubber	
Specific Gravity	1.04	
Extrusion Rate, g/min.	370	ASTM C-1183
1/8" orifice @ 50 psi		Modified
Temperature Range	-62°F to 350°F	
Intermittent Temperature Range	400°F	
Accelerated Weathering (10,000 hrs.)	No Change	QUV Weatherometer
Skin Over Time (min)	10*	MNA Method
Tack Over Time (min)	17*	ASTM C-679
Cure Rate	1/8" per 24hrs*	MNA Method
Tensile Strength (psi)	310	ASTM D-412
Elongation %	500	ASTM D-412
Durometer Shore A	26	ASTM C-661
Dielectric Strength kv/mm (v/mil)	20 (500)	
Dielectric Constant at 100 Hz	2.7 @ 60	
Shelf Life (months)	24	
Volatile Organic Content	30 gr./litre	

*All properties derived from lab conditions (77° F at 50% relative humidity)

Test results are averages obtained under laboratory conditions. Reasonable variations can be expected.

NOTE: This product is not recommended for use with pure oxygen systems.

IMPORTANT NOTICE: All statements and technical data contained herein are based on tests we believe to be reliable, but the accuracy of completeness thereof is not guaranteed. It is recommended that the buyer test this product to determine its suitability for his application before use. **SAF-T-LOK International Corporation** is not responsible for loss, claim or damages resulting from use of its