## SAF-T-LOK

300 Eisenhower Lane N. Lombard, IL 60148 (630)495-2001 <u>cs@saftlok.com</u> www.saftlok.com

### <u>HI-TEMP PIPE SEALANT</u>

**Technical Data Sheet** 

# **PRODUCT DESCRIPTION:**

*SAF-T-LOK Hi-Temp Pipe Sealant* was developed for use on hot pipes immediately after cutting threads. It does not flash off or vaporize. Hi-Temp TPS performs on all metals including stainless steel and aluminum and works on straight, non-jamming threads as well as NPT pipe connections. This pipe sealant begins curing immediately and is fully cured in 4 hours. After 8 hours, sealing pressure exceeds the burst strength rating of the pipe. Pipe larger than 1 inch in diameter may require more than 4 hours due to the larger gaps present in coarse pipe threads. Hi-Temp TPS does not attack paint.

# **GENERAL INFORMATION:**

**SAF-T-LOK** anaerobic adhesive/sealants are a specialized series of single component, solvent free compounds that are individually formulated for locking, sealing, retaining and bonding metal parts and assemblies.

Stable in the presence of air, these products cure when placed between two mating metal parts, forming a resilient, vibration-proof, bonded seal. *SAF-T-LOK* adhesive/sealants provide the user with additional performance characteristics, including resistance to corrosion or galvanic attack between dissimilar metals, as well as solvent resistance, while allowing disassembly with normal tools, if required.

## **PHYSICAL PROPERTIES:**

Color:	White
Specific Gravity:	1.15 gm/cc
Viscosity:	500,000 cps
Flash Point:	860°F
Temperature Range:	-65°F to +400°F
Storage Stability:	12 months @ <75°F

## **PERFORMANCE CHARACTERISTICS:**

Cure Speeds:	
50% Cure	4 Hours
90% Cure	8 Hours
Instant Sealing	>200 psig
Chemical Resistance:	Excellent

Note: This product is not recommended for use with pure oxygen systems.

**IMPORTANT NOTICE:** All statements and technical data contained herein are based on tests we believe to be reliable, but the accuracy of completeness thereof is not guaranteed. It is recommended that the buyer test this product to determine its suitability for his application before use. *SAF-T-LOK* International Corporation is not responsible for loss, claim or damages resulting from use of its products.

#### TECHNICAL SUPPORT

Our technical support team stands ready to assist you with your technical questions regarding your SAF-T-LOK products. On-site support when necessary within 24 hours.

#### PART NUMBERS

26832

#### TURNKEY SOLUTIONS

50ml

As an ISO 9001:2015 certifed company, SAF-T-LOK can design or refine products to fit your company's specific needs and requirements.

For more information on any of our products or services please visit us on the Web at: www.saftlok.com