

300 Eisenhower Lane N. Lombard, IL 60148 (630)495-2001 cs@saftlok.com www.saftlok.com

TRI-CURE III UV ADHESIVE

Technical Data Sheet

TECHNICAL SUPPORT

Our technical support team stand ready to assist you with your technical questions regarding your SAF-T-LOK products. On-Site support when necessary within 24 hours.

PART NUMBERS

30331 50gm 31351 1lb

TURNKEY SOLUTIONS

As an ISO 9001:2015 certifed company, SAF-T-LOK can design or refine products to fit your company's specific needs and requirements.

For more information on any of our products or services please visit us on the Web at: www.saftlok.com

PRODUCT DESCRIPTION:

SAF-T-LOK TRI-CURE III UV ADHESIVE is used for bonding and potting. It cures with UV light sources, as well as with heat and activator, and conforms to specific low viscosity assembly requirements. This Low viscosity adhesive provides high tensile strength bonds as well as high impact, peel and fatigue resistance on clear plastic or glass to like materials or to steel, aluminum, epoxy board, fiberglass, and phenolics.

PRODUCT CHARACTERISTICS:

Color:	Clear-Amber
Specific Gravity:	1.08 gm/cc
Viscosity:	300 cps
Flash Point:	200°F
Storage Stability:	12 months

PERFORMANCE CHARACTERISTICS:

UV Cure*:	10 seconds
Temperature Range:	-65°F to +350°F
Tensile Shear:	3,000 psi

*2 mil gap on glass, 7,000microwatts/cm long wave ultraviolet light (black light)

UV SOURCE: Long wave (250-350 nanometers) of at least 7,000microwatts/cm2 intensity. Speed of cure, and tack free surface are a function of the light used as shown in the above plot. For gaps over .05 inches, a 100,000microwatt/cm2 light is recommended. Potting depths over .15 inches require multiple applications.

APPLICATIONS: BRIDGING, POTTING, TACKING, & SEALING

*Jewelry Assembly *Lens Bonding

ACTIVATOR may be used to supplement UV cure where this light source is shadowed. Apply *SA Activator* liberally and allow solvent to evaporate. Assemble. Apply UV light to accelerate surface cure.

HEAT cure for 1 hour at 200°F or for 15 minutes at 300°F may prove an advantage for particular applications. UV light and heat may be combined, or heat and activator where heat sinks occur in assembly parts.

IMPORTANT NOTICE: All statements and technical data contained herein are based on tests we believe to be reliable, but the accuracy of completeness thereof is not guaranteed. It is recommended that the buyer test this product to determine its suitability for his application before use. **SAF-T-LOK International Corporation** is not responsible for loss, claim or damages resulting from use of its products.